



Deutsch: **Technisches Datenblatt** Viton® - FKM Moosgummi

<b>0580</b>	<b>Viton® - FKM Moosgummi, Stärke: 3,18 - 12,7 mm</b>	<b>Datum: 01.01.2016</b>
<b>Härte (DIN ISO 7619-1):</b>	10° - 15° Shore A	
<b>Farbe:</b>	schwarz	
<b>Zellart:</b>	geschlossenenzellig mit Außenhaut	
<b>Rohdichte (DIN ISO 1183):</b>	0,2 bis 0,3 g/ cm <sup>3</sup>	
<b>Temperaturbereich:</b>	-25 bis +200° C	
<b>Ozonbeständigkeit:</b>	sehr gut	
<b>Witterungsbeständigkeit:</b>	sehr gut	
<b>Mineralöl-, Kraftstoff-, Fett-, Kohlen-, Wasserstoff- und chlorierte Lösungsmittelbeständigkeit:</b>	sehr gut	
<b>Bemerkungen:</b>	RoHS, PHOS frei, kein IMDS-Eintrag vorhanden	

Jederzeitige Änderungen vorbehalten. Es obliegt dem Besteller, vor Verwendung des Produktes selbst zu prüfen, ob es sich auf mögliche anwendungswirksame Einflüsse für den von ihm vorgesehenen Verwendungszweck eignet. Alle in diesem technischen Datenblatt enthaltenen Angaben stellen Richtwerte dar.

RESOGOOGO® GmbH & Co KG  
Rolandskoppel 17, D-24784 Westerrönfeld  
Tel: +49-4331-43818-0  
Fax: +49-4331-43818-28

Mail: [post@resogoo.com](mailto:post@resogoo.com), [www.resogoo.com](http://www.resogoo.com)



English: **Technical data sheet**

**Viton® - FKM sponge**

---

<b>0580</b>	<b>Viton® - FKM sponge, thickness: 3,18 - 12,7 mm</b>	<b>date: 01.01.2016</b>
<b>hardness (DIN ISO 7619-1):</b>	10° - 15° Shore A	
<b>color:</b>	black	
<b>cell type</b>	closed celled covered with skin	
<b>density (DIN ISO 1183):</b>	0,2 bis 0,3 g/ cm <sup>3</sup>	
<b>temperature range:</b>	-25 to +200 °C,	
<b>ozone resistance:</b>	very good	
<b>weathering resistance:</b>	very good	
<b>mineral oil, fuel, grease, carbon-hydrogen and chlorinated solvent resistance:</b>	very good	
<b>remarks:</b>	RoHS, PHOS free, IMDS data not available	

---

We reserve the right to make changes at any time. Before using the product, it is the responsibility of the purchaser to check for himself whether it is suitable for his intended use with regard to possible influences affecting the application. All data contained in this technical data sheet are approximate values.

---

**RESOGOO® GmbH & Co KG**  
Rolandskoppel 17, D-24784 Westerrönfeld  
**Tel: +49-4331-43818-0**  
**Fax: +49-4331-43818-28**

Mail: [post@resogoo.com](mailto:post@resogoo.com), [www.resogoo.com](http://www.resogoo.com)